

ASPET AS 21C

PET

Dhunseri Ventures Limited

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	248	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.84	dl/g	-
Acetaldehyde	1	ppm	-
Color L	90	-	CIE
Color b	0.35	-	CIE
Crystallinity	50	%	-
Moisture Content	0.25	%	-

Characteristics**Processing**

Blow Molding

Applications

General Purpose, Packaging

Features

Copolymer

Regional Availability

Asia Pacific

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR