

Aspire™ T80

PET

Safripol (Pty) Ltd

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	254	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.8	dl/g	-
Acetaldehyde	1	ppm	-
Color L	80	-	CIE
Color b	0.5	-	CIE
Moisture Content	0.2	%	-

Characteristics**Processing**

Sheet Extrusion, Blow Molding, Thermoforming

Special Characteristics

Transparent

Features

High Gloss, Copolymer

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

Near East/Africa