

**Product Texts**

PET for multiple purpose made partially from renewable resources. The biobased carbon content (BCC) is 20 % (determined according to ASTM D6866).

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>250</b>	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	<b>1350</b>	kg/m <sup>3</sup>	ISO 1183
Biobased content	<b>20</b>	%	-
Intrinsic Viscosity	<b>0.77</b>	dl/g	-
Moisture Content	<b>0.4</b>	%	-
Bulk density	<b>870</b>	kg/m <sup>3</sup>	-

**Characteristics****Delivery form**

Pellets, White

**Certifications**

Contains renewable resources

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa