

FuTuRe PET 3325

PET

Indorama Ventures PCL

| Thermal properties | Value | Unit | Test Standard |
|--------------------------------------|--------------|-------------|----------------------|
| Other Standards^[5] | | | |
| Melting temperature, 10°C/min | 250 | °C | |

S: These properties are reported by the producer according standards that are different to our defaults.

| Other properties | Value | Unit | Test Standard |
|--------------------------------------|--------------|-------------------|----------------------|
| Intrinsic Viscosity | 0.74 | dl/g | - |
| Acetaldehyde | 0.6 | ppm | - |
| Color b | -2.5 | - | CIE |
| Crystallinity | 53 | % | - |
| Moisture Content | 0.15 | % | - |
| Bulk density | 900 | kg/m ³ | - |
| Other Standards^[5] | | | |
| Density | 1400 | kg/m ³ | |

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Injection Molding, Blow Molding

Special Characteristics

Transparent

Features

Barrier Properties, High Gloss, Copolymer

Certifications

Recycled Resin Content, Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, South and Central America