

Infinite S 80 FR

PET

Selenis Portugal, S.A.

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	255	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.8	dl/g	-
Acetaldehyde	1	ppm	-
Color L	78	-	CIE
Color b	1	-	CIE
Crystallinity	50	%	-
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	175	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.005	%	-

Characteristics**Processing**

Injection Molding, Blow Molding

Delivery form

Pellets

Special Characteristics

Transparent

Features

High Gloss, Low Odor, Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, South and Central America