

## Infinite S 84 FR

PET

Selenis Portugal, S.A.

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melting Temperature	255	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.84	dl/g	-
Acetaldehyde	1	ppm	-
Color L	78	-	CIE
Color b	1	-	CIE
Crystallinity	50	%	-
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	175	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.005	%	-

### Characteristics

#### Processing

Injection Molding, Blow Molding

#### Delivery form

Pellets

#### Special Characteristics

Transparent

#### Features

High Gloss, Low Odor, Copolymer

#### Certifications

Food contact, Food approval FDA 21 CFR

#### Regional Availability

North America, Europe, South and Central America