

Krupet-A Pellets black

PET

Steinbeis PolyVert GmbH

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|-------------------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 50 | g/10min | ISO 1133 |
| Temperature | 280 | °C | - |
| Load | 2.16 | kg | - |
| Other properties | | | |
| Density | 1370 | kg/m ³ | ISO 1183 |
| Intrinsic Viscosity | 0.7 | dl/g | - |
| Acetaldehyde | 5 | ppm | - |
| Color L | 39 | - | CIE |
| Color a | -1.5 | - | CIE |
| Color b | 0 | - | CIE |
| Moisture Content | 0.2 | % | - |
| Bulk density | 860 | kg/m ³ | - |

Characteristics

Delivery form

Pellets, Black

Regional Availability

Europe

Certifications

Recycled Resin Content