

Laser+® (B90B)

PET

DAK Americas LLC

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	241	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.84	dl/g	-
Acetaldehyde	2	ppm	-
Color L	78	-	CIE
Color b	-3	-	CIE
Crystallinity	40	%	-
Moisture Content	0.25	%	-
Bulk density	870	kg/m ³	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	150 - 165	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	250 - 280	°C	-

Characteristics**Processing**

Blow Molding

Delivery form

Pellets

Features

Barrier Properties, Copolymer

Chemical Resistance

Environmental Stress Crack Resistance

Certifications

Food contact, Food contact notification (FCN)

Applications

Packaging

Regional Availability

North America, South and Central America