

Octal PET RH02

PET

Octal Petrochemicals FZC

| Thermal properties | Value | Unit | Test Standard |
|-------------------------------|-------|------|----------------|
| ISO Data | | | |
| Melting temperature, 10°C/min | 247 | °C | ISO 11357-1/-3 |

| Other properties | Value | Unit | Test Standard |
|---------------------|-------|------|----------------|
| Humidity absorption | 0.1 | % | Sim. to ISO 62 |
| Intrinsic Viscosity | 0.8 | dl/g | - |
| Acetaldehyde | 1 | ppm | - |
| Color L | 76 | - | CIE |
| Color b | -0.5 | - | CIE |

Characteristics

Processing

Blow Molding

Delivery form

Pellets

Chemical Resistance

Oil Resistance

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Medical, Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa