

Octal PET WG02

PET

Octal Petrochemicals FZC

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	247	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Humidity absorption	0.1	%	Sim. to ISO 62
Intrinsic Viscosity	0.76	dl/g	-
Acetaldehyde	1	ppm	-
Color L	82	-	CIE
Color b	0.5	-	CIE

Characteristics

Processing

Blow Molding

Delivery form

Pellets

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa