

SKYLETE GE800

PETG

SK Chemicals

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	44	MPa	ISO 527
Yield strain	4.4	%	ISO 527
Stress at break	46	MPa	ISO 527
Strain at break	220	%	ISO 527
Flexural modulus, 23°C	1600	MPa	ISO 178
Flexural strength	60	MPa	ISO 178
Izod notched impact strength, +23°C	93	kJ/m ²	ISO 180/1A
ASTM Data			
Rockwell Hardness	R 105	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	64	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	76	°C	ISO 75-1/-2

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	1	%	ASTM D 1003
Light Transmittance	90	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ASTM D 792

Characteristics**Processing**

Additive Manufacturing

Special Characteristics

High impact or impact modified, Transparent

Chemical Resistance

General Chemical Resistance

Applications

Filament for 3D Printing

Regional Availability

North America, Europe, Asia Pacific, South and Central America