

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	8000	MPa	ISO 527
Stress at break	120	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Izod impact strength, +23°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	6	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	250	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1480	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.08	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 140	°C	-
Pre-drying - Time	4	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	120 - 140	°C	-
Feed temperature	50 - 70	°C	-
Holding pressure	60 - 100	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Europe