

Tarolox 111 G5 Y0

PET-GF25

Taro Plast S.p.A.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10200	MPa	ISO 527
Stress at break	100	MPa	ISO 527
Strain at break	1.8	%	ISO 527
Flexural modulus, 23°C	9400	MPa	ISO 178
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6.5	kJ/m ²	ISO 179/1eA
ASTM Data			
Izod Impact notched, 1/8 in	75	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	60	J/m	ASTM D 256
Temperature	-20	°C	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	256	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	232	°C	ISO 75-1/-2
Vicat softening temperature, B	235	°C	ISO 306
Coeff. of linear therm. expansion, parallel	33	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
Other properties			
Value			
Water absorption	0.05	%	Sim. to ISO 62
Density	1550	kg/m ³	ISO 1183

Characteristics**Delivery form**

Pellets

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Features

Low Odor

Applications

Electrical and Electronical

Regional Availability

Europe