

Matrixx 80S7301

PET-GF30

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	145	MPa	ASTM D 638
Flexural Modulus	8620	MPa	ASTM D 790
Izod Impact notched, 1/8 in	75	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	234	°C	ASTM D 648
DTUL @ 264 psi	210	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1560	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Regional Availability

North America