

PET-RG30

PET-GF30

Kingfa Sci. & Tech.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	140	MPa	ASTM D 638
Elongation at Break	2.3	%	ASTM D 638
Flexural Modulus	10480	MPa	ASTM D 790
Flexural Strength	210	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	76.9	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-
DTUL @ 66 psi	240	°C	ASTM D 648
DTUL @ 264 psi	225	°C	ASTM D 648
Electrical properties			
ASTM Data			
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.07	%	ASTM D 570
Density	1650	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

Electrical and Electronical

Delivery form

Pellets

Regional Availability

Asia Pacific

Special Characteristics

Flame retardant, Heat stabilized or stable to heat