

Product Texts

35% Glass Reinforced

ISO 1043 PET-GF35

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Density of melt	1350	kg/m ³	-
^[C] Thermal conductivity of melt	0.195	W/(m K)	-
^[C] Spec. heat capacity of melt	1670	J/(kg K)	-
^[C] Eff. thermal diffusivity	8.67E-8	m ² /s	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	13000	MPa	ISO 527
^[C] Stress at break	190	MPa	ISO 527
^[C] Strain at break	2.5	%	ISO 527
^[C] Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	50	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	255	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	235	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	250	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	25	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	40	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.3	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.1	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	30	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	130	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Electric strength	34	kV/mm	IEC 60243-1
^[C] Comparative tracking index	250	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.45	%	Sim. to ISO 62
^[C] Humidity absorption	0.18	%	Sim. to ISO 62
^[C] Density	1630	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Additives

Release agent

Delivery form

Pellets

Regional Availability

Europe, Asia Pacific

Other text information**Injection molding**[Injection Molding Recommendations](#)[Steel recommendations for molds screws and barrels](#)[Supporting document for Stanyl quality processing](#)