

Tarolox 111 G7

PET-GF35

Taro Plast S.p.A.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	13000	MPa	ISO 527
Stress at break	165	MPa	ISO 527
Strain at break	2.2	%	ISO 527
Flexural modulus, 23°C	10500	MPa	ISO 178
Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	11	kJ/m ²	ISO 179/1eA
ASTM Data			
Izod Impact notched, 1/8 in	90	J/m	ASTM D 256
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	256	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	230	°C	ISO 75-1/-2
Vicat softening temperature, B	240	°C	ISO 306
Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-
Limiting Oxygen Index	24	%	ASTM D 2863
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Electric strength	34	kV/mm	IEC 60243-1
Comparative tracking index	250	-	IEC 60112
Other properties			
Water absorption	0.05	%	Sim. to ISO 62
Density	1610	kg/m ³	ISO 1183

Characteristics**Delivery form**

Pellets

Features

Low Odor

Additives

Release agent

Chemical Resistance

General Chemical Resistance

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe