

**Iupilon TMB1615**

(PC+ABS)

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	11	cm <sup>3</sup> /10min	ISO 1133
Temperature	260	°C	-
Load	2.16	kg	-
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	260	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.2	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	5300	MPa	ISO 527
Yield stress	67	MPa	ISO 527
Yield strain	3.8	%	ISO 527
Strain at break	8	%	ISO 527
Flexural modulus, 23°C	4800	MPa	ISO 178
Flexural strength	108	MPa	ISO 178
Charpy impact strength, +23°C	130	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	90	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	1.0	mm	-
Yellow Card available	yes	-	-

Other properties	Value	Unit	Test Standard
Water absorption	0.2	%	Sim. to ISO 62
Density	1290	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 8	h	-
Mold temperature	50 - 70	°C	-
Zone 1	230 - 270	°C	-
Zone 2	230 - 270	°C	-
Zone 3	230 - 270	°C	-
Nozzle temperature	230 - 270	°C	-

**Characteristics****Processing**

Injection Molding

**Additives**

Flame retarding agent

**Special Characteristics**

Flame retardant

**Applications**

General Purpose

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa