

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>4.5</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Melting Temperature	<b>120</b>	°C	ASTM D 3418
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	<b>7</b>	%	ASTM D 1003
<b>Other properties</b>			
Density	<b>925</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Film Properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield, MD	<b>7.58</b>	MPa	ASTM D 882
Elongation at Break, MD	<b>780</b>	%	ASTM D 882
Type of extrusion	<b>cast</b>	-	-
Thickness of specimen	<b>0.0508</b>	mm	-

**Characteristics**

**Processing**

Other Extrusion, Coating

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Barrier Properties, Low Neck-In

**Regional Availability**

North America