

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	18	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	128	°C	ASTM D 3418
Other properties			
Density	952	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Melt temperature	232 - 260	°C	-

Characteristics

Processing

Fiber Extrusion, Other Extrusion, Coating

Regional Availability

North America

Features

Barrier Properties