

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.4	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	117	°C	ASTM D 3418
Optical properties			
ASTM Data			
Gloss	81	-	ASTM D 2457
Haze	2.9	%	ASTM D 1003
Other properties			
Density	923	kg/m ³	ASTM D 792
Film Properties			
ASTM Data			
Tensile Strength at Break, MD	37.9	MPa	ASTM D 882
Tensile Strength at Break, TD	34.5	MPa	ASTM D 882
Elongation at Break, MD	700	%	ASTM D 882
Elongation at Break, TD	800	%	ASTM D 882
Type of extrusion	cast	-	-
Thickness of specimen	0.0508	mm	-

Characteristics

Processing

Film Extrusion

Certifications

Food contact

Special Characteristics

Transparent

Applications

Packaging

Features

Heat Sealable, High Gloss

Regional Availability

North America