

Borlink™ LE0511

PE

Borealis A/S

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	11	MPa	ASTM D 638
Elongation at Break	250	%	ASTM D 638

Electrical properties	Value	Unit	Test Standard
Other Standards^{S1}			
Volume Resistivity	50	Ohm*cm	ASTM D 991

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ASTM D 792

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	115 - 125	°C	-

Characteristics**Processing**

Wire/Cable Extrusion

Delivery form

Black

Special Characteristics

Increased electrical conductivity

Features

Crosslinkable, Thermal Stability

Applications

Electrical and Electronical

Regional Availability

North America, South and Central America