

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	15	MPa	ISO 527
Strain at break	200	%	ISO 527

Electrical properties	Value	Unit	Test Standard
Other Standards^[5]			
Volume resistivity	1	Ohm*m	ISO 3915

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	60	°C	-
Pre-drying - Time	4	h	-
Melt temperature	120 - 130	°C	-

Characteristics

Processing
Wire/Cable Extrusion

Delivery form
Black

Special Characteristics
Increased electrical conductivity

Features
Crosslinkable

Applications
Electrical and Electronical

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa