

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	15	MPa	ISO 527
Strain at break	150	%	ISO 527

Electrical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Volume resistivity	1	Ohm*m	ISO 3915

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1140	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	60	°C	-
Pre-drying - Time	4	h	-
Melt temperature	120 - 135	°C	-

## Characteristics

### Processing

Wire/Cable Extrusion

### Delivery form

Black

### Special Characteristics

Increased electrical conductivity

### Features

Crosslinkable, Thermal Stability

### Applications

Electrical and Electronical

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa