

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	15	MPa	ISO 527
Strain at break	150	%	ISO 527

Electrical properties	Value	Unit	Test Standard
Other Standards^[5]			
Volume resistivity	1	Ohm*m	ISO 3915

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	60	°C	-
Pre-drying - Time	4	h	-
Melt temperature	120 - 135	°C	-

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Black

Special Characteristics

Increased electrical conductivity

Features

Crosslinkable, Thermal Stability

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa