

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.2	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	17	MPa	ASTM D 638
Elongation at Break	400	%	ASTM D 638
Electrical properties			
ASTM Data			
Dissipation Factor, 60 Hz	0.0005	-	ASTM D 150
Dielectric Constant, 60 Hz	2.3	-	ASTM D 150
Other properties			
Density	923	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Type of extrusion	wire/cable	-	-
Melt temperature	125 - 135	°C	-

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Natural Color

Features

Crosslinkable

Applications

Electrical and Electronical

Regional Availability

North America, South and Central America