

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|-------------------|-------------------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 0.8 | g/10min | ISO 1133 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Tensile Strength | 17 | MPa | ISO 527 |
| Strain at break | 450 | % | ISO 527 |
| Other properties | | | |
| Density | 922 | kg/m ³ | ISO 1183 |
| Processing Recommendation Extrusion | | | |
| Type of extrusion | wire/cable | - | - |
| Melt temperature | 125 - 135 | °C | - |

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Natural Color

Features

Crosslinkable

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa