

**Borlink™ LH4201R**

PE

Borealis A/S

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>2.8</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Strength	<b>17</b>	MPa	ISO 527
Strain at break	<b>450</b>	%	ISO 527
<b>Other properties</b>			
Density	<b>924</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Extrusion</b>			
Melt temperature	<b>125 - 135</b>	°C	-

**Characteristics****Processing**

Wire/Cable Extrusion

**Delivery form**

Natural Color

**Features**

Crosslinkable

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa