

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Strength	17	MPa	ISO 527
Strain at break	450	%	ISO 527
<b>Other properties</b>			
Density	922	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Extrusion</b>			
Melt temperature	125 - 135	°C	-

**Characteristics**

**Processing**

Wire/Cable Extrusion

**Delivery form**

Natural Color

**Features**

Crosslinkable

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa