

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Strength	17	MPa	ISO 527
Strain at break	450	%	ISO 527
Other properties			
Density	922	kg/m ³	ISO 1183
Processing Recommendation Extrusion			
Melt temperature	125 - 135	°C	-

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Natural Color

Features

Crosslinkable

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa