

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.6	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Shore D hardness	53	-	ISO 7619-1
Thermal properties			
ISO Data			
Oxygen index	28	%	ISO 4589-1/-2
Other properties			
Density	1160	kg/m ³	ISO 1183
Processing Recommendation Extrusion			
Type of extrusion	wire/cable	-	-
Pre-drying - Temperature	70	°C	-
Pre-drying - Time	4	h	-
Zone 1	160	°C	-
Zone 2	170	°C	-
Zone 3	180	°C	-
Zone 4	190	°C	-
Nozzle temperature	190	°C	-

Characteristics

Processing

Wire/Cable Extrusion, Other Extrusion

Delivery form

Natural Color

Special Characteristics

Flame retardant, Halogen-free, U.V. stabilized or stable to weather

Features

Low Smoke

Applications

Electrical and Electronical

Regional Availability

Europe