

CoReg BH

PE

ConVerta GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	440	MPa	ISO 527
Tensile Strength	15.5	MPa	ISO 527
Charpy notched impact strength, +23°C	80	kJ/m ²	ISO 179/1eA
Other properties			
Density	925	kg/m ³	ISO 1183
Bulk density	575	kg/m ³	-

Characteristics**Delivery form**

Granules

Regional Availability

Europe

Certifications

Recycled Resin Content