

CoReg SF

PE

ConVerta GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.4	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	756	MPa	ISO 527
Tensile Strength	19.3	MPa	ISO 527
Charpy notched impact strength, +23°C	4.1	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ISO 1183
Bulk density	575	kg/m ³	-

Characteristics**Delivery form**

Granules

Regional Availability

Europe

Certifications

Recycled Resin Content