

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	0.7	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.1	kg	-
<b>Optical properties</b>			
<b>ASTM Data</b>			
Gloss	66	-	ASTM D 2457
Haze	9	%	ASTM D 1003
<b>Other properties</b>			
Density	917	kg/m <sup>3</sup>	ASTM D 792
<b>Film Properties</b>			
<b>ISO Data</b>			
Stress at yield, parallel	5.2	MPa	ISO 527-3
Stress at yield, normal	8	MPa	ISO 527-3
Stress at break, parallel	38.9	MPa	ISO 527-3
Stress at break, normal	34.7	MPa	ISO 527-3
Maximum strain, parallel	610	%	ISO 527-3
Maximum strain, normal	630	%	ISO 527-3
Dart drop A	1100	g	ISO 7765-1
Type of extrusion	blown	-	-
Thickness of specimen	0.05	mm	-

## Characteristics

### Processing

Blown Film Extrusion, Film Extrusion

### Delivery form

Pellets, White

### Additives

Antiblocking agent

### Features

Blending Resin, Heat Sealable, Low Odor, Copolymer, Octene Copolymer

### Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN)

### Applications

Packaging

### Regional Availability

North America, Europe, Asia Pacific, South and Central America