

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.9	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	1.9	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	109	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	109	°C	ASTM D 3418
Vicat Temperature	94	°C	ASTM D 1525
Other properties			
Density	920	kg/m ³	ISO 1183
Density	920	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Melt temperature	180 - 235	°C	-

Characteristics

Processing

Blow Molding

Additives

Release agent

Chemical Resistance

Environmental Stress Crack Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Medical, Packaging

Regional Availability

North America