

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|-----------|-------------------|----------------|
| ISO Data | | | |
| Melt flow index, MFI | 1.9 | g/10min | ISO 1133 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |
| ASTM Data | | | |
| Melt Flow Index, MFI | 1.9 | g/10min | ASTM D 1238 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |
| Thermal properties | | | |
| ISO Data | | | |
| Melting temperature, 10°C/min | 109 | °C | ISO 11357-1/-3 |
| ASTM Data | | | |
| Melting Temperature | 109 | °C | ASTM D 3418 |
| Vicat Temperature | 94 | °C | ASTM D 1525 |
| Other properties | | | |
| Density | 920 | kg/m ³ | ISO 1183 |
| Density | 920 | kg/m ³ | ASTM D 792 |
| Processing Recommendation Extrusion | | | |
| Melt temperature | 180 - 235 | °C | - |

Characteristics

Processing

Blow Molding

Additives

Release agent

Chemical Resistance

Environmental Stress Crack Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Medical, Packaging

Regional Availability

North America