

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.9	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	1.9	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	109	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	109	°C	ASTM D 3418
Vicat Temperature	96	°C	ASTM D 1525
<b>Other properties</b>			
Density	920	kg/m <sup>3</sup>	ISO 1183
Density	920	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Melt temperature	180 - 235	°C	-

## Characteristics

### Processing

Injection Molding

### Additives

Release agent

### Chemical Resistance

Environmental Stress Crack Resistance

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Medical, Packaging

### Regional Availability

North America, Europe, Asia Pacific, South and Central America