

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.85	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	123	°C	ASTM D 3418
Vicat Temperature	106	°C	ASTM D 1525
Optical properties			
ASTM Data			
Gloss	33	-	ASTM D 2457
Haze	20	%	ASTM D 1003
Other properties			
Density	920	kg/m ³	ASTM D 792
Film Properties			
ASTM Data			
Tensile Strength at Yield, MD	11.9	MPa	ASTM D 882
Tensile Strength at Yield, TD	12.4	MPa	ASTM D 882
Tensile Strength at Break, MD	43.6	MPa	ASTM D 882
Tensile Strength at Break, TD	36	MPa	ASTM D 882
Elongation at Break, MD	480	%	ASTM D 882
Elongation at Break, TD	620	%	ASTM D 882
Type of extrusion	blown	-	-
Thickness of specimen	0.025	mm	-

Characteristics

Processing

Blown Film Extrusion, Film Extrusion

Delivery form

Pellets, White

Special Characteristics

High impact or impact modified

Features

Low Odor, Copolymer

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America