

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	103	°C	ASTM D 3418
Vicat Temperature	86	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	911	kg/m³	ASTM D 792

Film Properties	Value	Unit	Test Standard
ISO Data			
Stress at yield, parallel	7.1	MPa	ISO 527-3
Stress at break, parallel	18.1	MPa	ISO 527-3
Maximum strain, parallel	690	%	ISO 527-3
Type of extrusion	cast	-	-

Characteristics

Processing

Other Extrusion, Coating

Features

Heat Sealable

Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN)

Regional Availability

Europe, Near East/Africa