

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.5	g/10min	ISO 1133
Optical properties			
ASTM Data			
Gloss	93	-	ASTM D 2457
Haze	1	%	ASTM D 1003
Other properties			
Density	918	kg/m ³	ISO 1183
Film Properties			
ISO Data			
Stress at break, parallel	40	MPa	ISO 527-3
Stress at break, normal	20	MPa	ISO 527-3
Maximum strain, parallel	300	%	ISO 527-3
Maximum strain, normal	400	%	ISO 527-3
Type of extrusion	cast	-	-
Thickness of specimen	0.02	mm	-
Processing Recommendation Extrusion			
Melt temperature	230 - 280	°C	-

Characteristics

Processing

Film Extrusion

Applications

Monofilament

Features

Low Gel, Copolymer, Hexene Copolymer

Regional Availability

Europe