

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.2	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	700	MPa	ISO 527
Yield stress	18	MPa	ISO 527
Stress at break	54	MPa	ISO 527
Strain at break	500	%	ISO 527
Other properties			
Density	937	kg/m ³	ISO 1183

Characteristics

Processing

Pipe/Tube Extrusion

Delivery form

Natural Color

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe