

Evolue® H SP50800P

PE

Prime Polymer Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	135	g/10min	ISO 1133
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	124	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	124	°C	ASTM D 3418
Other properties			
Density	951	kg/m ³	ISO 1183

Characteristics**Delivery form**

Powder

Regional Availability

North America, Asia Pacific