

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	19	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	10.3	MPa	ASTM D 638
Thermal properties			
ASTM Data			
Melting Temperature	114	°C	ASTM D 3418
Vicat Temperature	95	°C	ASTM D 1525
Other properties			
Density	918	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Features

Thermal Stability, Copolymer, Hexene Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa