

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	19	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Other properties			
Density	918	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion, Coating

Features

Thermal Stability, Copolymer, Hexene Copolymer

Certifications

Food contact

Applications

Building Construction, Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa