

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Melt Flow Index, MFI	0.2	g/10min	JIS K 7210
Temperature	190	°C	-
Load	2.16	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Tensile Strength at Break	34	MPa	JIS K 7113
Elongation at Break	800	%	JIS K 7113
Flexural Modulus	130	MPa	ASTM D 747
Shore D Hardness	49	-	JIS K 7215

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Melting Temperature	101	°C	DSC

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Density	912	kg/m <sup>3</sup>	JIS K 7112

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Delivery form

Pellets, White

### Special Characteristics

High impact or impact modified

### Features

Foamable, Low Odor

### Certifications

Food contact, Food approval FDA 21 CFR

### Regional Availability

North America, Europe, Asia Pacific