

Product Texts

GX5110 contains 100% of recycled PE material.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.3	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	325	MPa	ISO 527
Yield stress	11	MPa	ISO 527

Other properties

	Value	Unit	Test Standard
Density	925	kg/m ³	ISO 1183
Recycled resin content	100	%	-

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion

Delivery form

Pellets, Natural Color

Special Characteristics

Transparent

Features

Blending Resin

Certifications

Recycled Resin Content, Post-Consumer Recyclate

Applications

Packaging

Regional Availability

Europe