

ISOPLAS P602

PE

MICROPOL - Stamford Products Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	29	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	128	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	956	kg/m ³	ISO 1183

Characteristics**Applications**

Medical

Regional Availability

Europe