

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.4	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	62	MPa	ISO 527
Yield stress	4	MPa	ISO 527
Yield strain	14.5	%	ISO 527
Shore A hardness	90	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	96	°C	ISO 11357-1/-3
Vicat softening temperature, A	70	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	924	kg/m ³	ISO 1183

Characteristics

Processing

Blown Film Extrusion, Film Extrusion, Profile Extrusion, Sheet Extrusion, Coating, Blow Molding

Delivery form

Pellets

Features

Anti Slip, Low Odor, Thermal Stability, Weldable, Copolymer

Chemical Resistance

Acid Resistance, Alkali Resistance, Environmental Stress Crack Resistance, Solvent Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa