

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	1.8	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Characteristics**Processing**

Blown Film Extrusion

Features

Blending Resin, Good Adhesion

Delivery form

Granules, Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa