

## Lushan DE-1

PE

Guangzhou Lushan New Materials Co., Ltd

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>600</b>	MPa	ISO 178
<b>ASTM Data</b>			
Tensile Strength	<b>22</b>	MPa	ASTM D 638
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Melting Temperature	<b>130</b>	°C	ASTM D 3418
<b>Other properties</b>			
Moisture Content	<b>0.07</b>	%	-
Density	<b>940</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Coating

### Chemical Resistance

Oil Resistance

### Delivery form

Powder

### Regional Availability

Asia Pacific

### Features

Good Adhesion